PRODUCT IMAGE

VGLOVE













Left/Right side





Material	Artificial Nitrile rubber.	
Species	No unpasteurized flour. Used for both hands; surface of rough fingertips; car wrist trim; White or colored (Blue, Light blue,)	
Quality standards	Compliant with ASTM D6319 standards Manufactured according to ISO 9001: 2008 quality management system, ISO 13485: 2003. ISO 22000: 2005. Made from 100% nitrile (Acrylonitrile-Butadiene)	
Size of gloves	Extra-small, Small, Medium, Large, Extra-large. Size is marked on the box with black ink.	
Preservation	Store in a cool, dry place, temperature not higher than 30 ° C.	
Expiry date	3 years from the date of manufacture.	

SIZE

SLZE	Standard		
SIZE	VRG OPENING	ASTM D6319	
Length (mm)	230 min	220 min (XS, S) 230 min (M, L, XL)	
Width (mm)	$75 \pm 5 \text{ (XS)}$	$70 \pm 10 (XS)$	
	$85 \pm 5 \text{ (S)}$	$80 \pm 10 (S)$	
	$95 \pm 5 (\mathrm{M})$	$95 \pm 10 (M)$	
	$105 \pm 5 (L)$	$110 \pm 10 (L)$	
	$115 \pm 5 (\mathrm{XL})$	$120 \pm 10 \text{ (XL)}$	
Thickness (mm)	Fingers: 0. 08 mm min Palm: 0.06 mm min	Fingers: 0.05 mm min Palm: 0.05 mm min	

PHYSICAL AND CHEMICAL INDICATORS

	Tensile strength (MPA) Pre-aging: 18Mpa min After aging: 20Mpa min	Tensile strength (MPA) Pre-aging: 14Mpa min After aging: 14Mpa min	
Tensile			
	Elongation at break (%) Before aging: 600% min	Elongation at break (%) Before aging: 500% min	
	After aging: 500% min	After aging: 400% min	
Powder content	Maximum 2 mg / glove		
Protein content	No protein		